




PRODOTTI CERTIFICATI EDP  
Criteri Ambientali Minimi (CAM)



Disponibile  
a richiesta  
Available  
upon request  
(non / not standard)



Nei disegni A o B indicano il lato preverniciato desiderato.  
In the drawings A or B show the wished pre-painted side.

## Caratteristiche tecniche - Datasheet

### Dimensioni:

larghezza 1000 (mm). Lunghezza a richiesta da produzione in continuo.

### Spessore di poliuretano fuori greca (S):

40 - 50 - 60 - 80 - 100 - 120 - 140 (mm) spessori non standard sono fornibili a richiesta previo accordo sui quantitativi minimi.

### Supporto esterno:

acciaio zincato, acciaio zincato preverniciato o plastificato; acciaio inox; alluminio naturale.

### Isolamento con schiumatura in continuo:

Resine poliuretatiche (PUR) e (PIR - non standard su richiesta), densità  $39 \pm 2 \text{ Kg/m}^3$  Valore dichiarato di trasmittanza termica per un pannello dopo 25 anni dalla sua messa in opera, (Appendice C - EN 13165)

Valore di conducibilità termica iniziale:  $\lambda = 0,020 \text{ W/(mK)}$

### Trattamenti protettivi per supporto esterno:

Preverniciatura con poliestere, superpoliestere (HD), PVDF, poliuretatici PUR/PA, plastisol, pvc plastificato con spessori compresi tra  $15 \mu\text{m}$  a  $200 \mu\text{m}$ . (vedi pag.79).

**Dimensions:** width (mm) 1000. Length upon request from continuous production process.

### Thicknesses: (S)

40 - 50 - 60 - 80 - 100 - 120 - 140 (mm) panels of non standard thicknesses can be supplied upon request previous agreement on minimum quantities.

### Supports:

galvanized steel, galvanized pre-painted or plastified steel; stainless steel; natural or pre-painted aluminium.

### Insulation through continuous foaming process of:

Polyurethane resins (PUR) and (not standard) polyisocyanurate foams (PIR), density  $39 \pm 2 \text{ Kg/m}^3$  Declared value of thermal transmittance for a panel after 25 years of its installation, (Appendix C - EN 13165) Initial value of thermal conductivity:  $\lambda = 0.020 \text{ W/(mK)}$

### Protective treatments for external support available:

Pre-painting with polyester, superpolyester (HD), PVDF, polyurethane PUR/PA, plastisol, plasticized PVC with thicknesses ranging from  $15 \mu\text{m}$  to  $200 \mu\text{m}$ . (see page 79).

Coefficiente di dispersione termica Coefficient of heat loss		
Spessore Thickness	Trasmittanza Trasmittance <b>EN UNI 14509</b>	Trasmittanza Trasmittance (8 gg / 8 days)*
(mm)	$U = \text{W/m}^2\text{K}$	$U = \text{W/m}^2\text{K}$
30	0,69	0,64
35	0,60	0,56
40	0,53	0,49
50	0,43	0,40
60	0,36	0,33
80	0,27	0,25
100	0,22	0,20
120	0,18	0,17
140	0,15	0,14

Calcoli effettuati su pannello con paramenti di acciaio 0,4 + 0,4 mm  
\* (a 8 giorni da produzione / 8 days from production)





Il fissaggio è il punto di forza del sistema Air-fix™ - permette di creare una parete ventilata senza forare i pannelli coibentati metallici pur mantenendo caratteristiche meccaniche di adeguata resistenza alle sollecitazioni, in questo modo il sistema riduce sensibilmente la presenza di ponti termici che possono presentarsi nella parete. Air-fix™, (nome prodotto che si ispira alle sue proprietà: fissaggio asciutto e ventilazione) senza fori passanti può collegare gres porcellanato, rivestimenti in legno o metallici e policarbonato.

*The fixing is the most important element of Air-fix™. Allows to create a ventilated facade without drilling insulated metal panels and maintaining appropriate mechanical characteristics of resistance to stress. The system significantly reduces the presence of thermal bridges in the wall. Air-fix™, (product name is inspired by its properties: ventilation and safe fixing dry) without holes can be combined with the porcelain gres, and wood paneling or metallic, and polycarbonate.*

In basso, viene riportato il rapporto di prova con relativo schema di carico. I valori di portata possono cambiare in maniera significativa al variare delle condizioni iniziali di progetto (luce di campata, durata di applicazione del carico: breve, lungo termine o permanente; spessori della lamiera esterna ed interna, temperature interne ed esterne, larghezza di appoggio, condizione di stato limite del pannello e tipo materiale). In questo caso i valori generati considerano lo spessore 5/10 interno ed esterno dei supporti metallici – acciaio zincato preverniciato, la larghezza dell'appoggio a 100 mm, carico lungo termine, stato limite di servizio (SLS 1/100° di L - rif. Punto E.5.4 – UNI EN 14509) - Δt 20°c.

**Approfondimenti sul rapporto di prova:**

Il rapporto di prova viene fornito a titolo puramente indicativo. Valori e formule non debbono essere utilizzati per stabilire o calcolare la portata del pannello. Sarà onere e cura del cliente e/o del progettista la redazione di calcoli appropriati con specifico riferimento al singolo impiego. Gli spessori e la qualità di acciaio indicati sul rapporto di prova non rappresentano uno standard di prodotto poichè la combinazione di spessori e materiali viene determinata dal cliente in base alle proprie esigenze di carattere tecnico pertanto il cliente e/o il progettista sono tenuti a specificare spessore, qualità e tipo di materiali che il produttore dovrà impiegare nella costruzione dei pannelli.

<b>CARICO MASSIMO UNIFORMEMENTE DISTRIBUITO (daN/m<sup>2</sup>) - FRECCIA ≤1/100 L</b>										
<b>MAXIMUM UNIFORMLY DISTRIBUTED LOAD (daN/m<sup>2</sup>) · DEFLECTION ≤1/100 L</b>										
Spessore Thickness (mm)	Distanza tra gli appoggi "L" in metri / Pitch "L" in metres between the supports									
	1.50	2.00	2.50	3.00	3.50	4.00	4.50	5.00	5.50	6.00
40	470	226	132	86	60	43	32	24	19	15
50	522	261	159	107	76	57	43	34	26	21
60	573	296	185	127	93	70	55	43	35	28
80	672	365	237	169	127	99	79	64	52	43
100	712	443	289	111	162	128	104	85	71	60
120	713	501	341	253	196	158	129	108	91	77
140	714	536	393	295	232	188	155	130	111	95
Spessore Thickness (mm)	Distanza tra gli appoggi "L" in metri / Pitch "L" in metres between the supports									
	1.50	2.00	2.50	3.00	3.50	4.00	4.50	5.00	5.50	6.00
40	643	471	371	265	191	144	113	91	74	62
50	671	492	386	318	236	178	139	111	91	76
60	690	512	402	331	281	212	165	133	109	91
80	714	546	435	357	302	262	219	175	144	120
100	732	557	455	374	314	274	241	212	179	149
120	730	558	456	376	318	275	245	218	196	175
140	728	559	457	378	320	278	247	220	198	179

**Test report analysis:**

The report test given above is provided for information purposes only. Values and formulas should not be used to determine or calculate the flow rate of the panel. It is the responsibility and care of the customer and/or designer to draft appropriate calculations with specific reference for individual uses. The thicknesses and quality of steel defined in the report test above, does not represent a standard of product as the combination of thicknesses and materials is determined by the customer according to their technical requirements, therefore the customer and/or the designer are required to specify thickness, quality and type of materials that the producer will use in the construction of the panels. The test report issued in this page gives load diagram and flow rate values. The flow values may change significantly to varying of the initial conditions of the project (light span, duration of load application: short, long term or permanent; thickness of sheet metal, interior and exterior, internal and external temperatures, width of support, condition of limit state of the panel and material type). In this case, the values generated consider the thickness of 5/10 interior and exterior of the metallic supports - prepainted galvanized steel, the width of the support to 100 mm, long-term load, serviceability limit state (SLS 1/100 ° L - ref. point E.5.4 - UNI EN 14509) - Δt 20°c